

ProVantage Komiwhite



Benefits

- High compression strength thanks to unique sheet anisotropy and fibre
- Improved smooth surface
- Optimum runnability and processing properties
- Superior appearance for high-quality printing
- Bleached top sheet ensures brilliant printability

End-uses

- Food & beverage packaging
- Promotional packaging
- Industrial packaging



Food Contact	ISO 9001	ISO 14001	OHSAS 18001	FSC®	PEFC™
•	•	•	•	•	•

Typical Values*

Properties	Method	Unit of measure	Substance (lb/1000 ft ²)						
			21.5	23.6	25.6	27.7	32.8	35.8	41.0
Moisture (average)	On-line	%	7.2	7.3				7.4	
Caliper	ISO 534	pt	4.92	5.51	6.10	6.50	7.87	8.46	9.65
Bursting strength	ISO 2759	lbf/in ²	63.8	75.4	83.4	92.1	108.8	118.9	130.5
SCT _{CD}	ISO 9895	lbf/inch	12.0	14.8	15.7	17.1	20.3	21.7	24.6
Scott plybond	TAPPI 569	ft . lbs/in ²	0.15		0.14				
Cobb ₆₀ (top)	ISO 535	g/m ²	32			31			
Cobb ₆₀ (bottom)		g/m ²	100	43			44		
Cobb ₁₈₀₀ (top)		g/m ²	95	100	105	110	120	125	
Brightness (top)	ISO 2470	%	75			76			
Bendtsen roughness (top)	ISO 8791-2	ml/min	190	240	260	290	370	430	460



Issued from 01.01.2021,
latest version available on
www.mondigroup.com

Test conditions:
Typical values after conditioning,
measured at 50 ± 2% RH and 23 ± 1°C
(ISO 187:1990)

* computed based on SI units

WWF's Environmental Paper Company Index: Mondi's constant high packaging score increased from 73.7% in 2013 to 85.7% in 2019.