

## ProVantage Komiwhite



### Benefits

- High compression strength thanks to unique sheet anisotropy and fibre
- Improved smooth surface
- Optimum runnability and processing properties
- Superior appearance for high-quality printing
- Bleached top sheet ensures brilliant printability

### End-uses

- Food & beverage packaging
- Promotional packaging
- Industrial packaging



Food Contact	ISO 9001	ISO 14001	OHSAS 18001	FSC®	PEFC™
•	•	•	•	•	•

### Typical Values

Properties	Method	Unit of measure	Substance (g/m <sup>2</sup> )						
			105	115	125	135	160	175	200
Moisture (average)	Online	%	7.2	7.3				7.4	
Caliper	ISO 534	µm	125	140	155	165	200	215	245
Bursting strength	ISO 2759	kPa	440	520	575	635	750	820	900
SCT <sub>CD</sub>	ISO 9895	kN/m	2.10	2.60	2.75	3.00	3.55	3.80	4.30
Scott plybond	TAPPI 569	J/m <sup>2</sup>	315			300			
Cobb <sub>60</sub> (top)	ISO 535	g/m <sup>2</sup>	32			31			
Cobb <sub>60</sub> (bottom)		g/m <sup>2</sup>	100	43			44		
Cobb <sub>1800</sub> (top)		g/m <sup>2</sup>	95	100	105	110	120	125	
Brightness (top)	ISO 2470	%	75			76			
Bendtsen roughness (top)	ISO 8791-2	ml/min	190	240	260	290	370	430	460

	<p>Issued from 01.01.2021, latest version available on <a href="http://www.mondigroup.com">www.mondigroup.com</a></p>	<p><b>Test conditions:</b> Typical values after conditioning, measured at 50 ± 2% RH and 23 ± 1°C (ISO 187:1990)</p>
--	-------------------------------------------------------------------------------------------------------------------------------	----------------------------------------------------------------------------------------------------------------------------------

**WWF's Environmental Paper Company Index:** Mondi's constant high packaging score increased from 73.7% in 2013 to 85.7% in 2019.